



TYPICAL PROPERTIES & SPECIFICATIONS SHEET

conductive containers, inc.

DESCRIPTION: Conductive Styrene

APPLICATION: Thermoforming

CCI PART NUMBER: CCI 24 STY PC

PROPERTY	VALUE (U.S.)	TEST METHOD
Surface Resistivity	10 ⁴ - 10 ⁷	-----
Expected Range	10 ³ - 10 ⁸ Ohms	-----
Static Decay Rate (5KV)	< .01 Sec @ 10% RH	-----
Specific Gravity	1.09	ASTM D-792
Flexural Modulus	220,000 psi	ASTM D-790B
Tensile Elongation (Break)	40%	ASTM D-638
Izod Notched Impact	5 ft-lbs/in	ASTM D-256A
Heat Deflection Temp @ 264 psi	154 °F	ASTM D-648

CHARACTERISTICS:

- Available in black only
- Gauge: 0.013” - 0.125”

All values are for pre-formed materials. Electrical values will vary with each individual design.

All information, recommendations and suggestions appearing in this bulletin concerning the use of our products are based upon tests and data believed to be reliable; however, it is the user's responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee, expressed or implied, is made by Conductive Containers, Inc. as to the effects of such use or the results to be obtained, nor does Conductive Containers, Inc. assume any liability arising out of use, by others, of the products referred to herein. Nor is the information herein to be construed as absolutely complete since additional information may be necessary or desirable, when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent.